



TITLE:

Synthesis of through-space conjugated polymers containing the pseudo-ortho-linked [2.2]paracyclophane moiety

AUTHOR(S):

Morisaki, Yasuhiro; Wada, Naoki; Arita, Manabu; Chujo, Yoshiki

CITATION:

Morisaki, Yasuhiro ...[et al]. Synthesis of through-space conjugated polymers containing the pseudo-ortho-linked [2.2]paracyclophane moiety. Polymer Bulletin 2009, 62(3): 305-314

ISSUE DATE:

2009-03

URL:

<http://hdl.handle.net/2433/123391>

RIGHT:

Copyright © 2009 Springer; This is not the published version. Please cite only the published version.; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。

Synthesis of Through-space Conjugated Polymers Containing the Pseudo-*ortho*-linked [2.2]Paracyclophane Moiety

Yasuhiro Morisaki (✉), Naoki Wada, Manabu Arita, Yoshiki Chujo (✉)

Department of Polymer Chemistry, Graduate School of Engineering, Kyoto University, Katsura, Nishikyo-ku, Kyoto 615-8510, Japan

E-mail: ymo@chujo.synchem.kyoto-u.ac.jp or chujo@chujo.synchem.kyoto-u.ac.jp; Fax: +81 75 383 2605

Received: /Revised version: / Accepted:

Summary

New through-space conjugated polymers comprising the pseudo-*ortho*-linked [2.2]paracyclophane moiety were synthesized by the Sonogashira coupling reaction. All the synthesized polymers were soluble in common organic solvents and could form thin films. The UV-vis absorption spectra of the synthesized polymers revealed an extension of the conjugation length owing to the through-space interactions. The polymers exhibited a blue-light emission in both solution and film states.

Introduction

[2.2]Paracyclophane has a compelling molecular structure consisting of two co-facial benzene rings in close proximity (ca. 2.8–3.1 Å) fixed by two ethylene chains [1]. The transannular electronic interaction between the co-facial benzene rings of [2.2]paracyclophane has attracted considerable attention [2], and a number of [2.2]paracyclophane derivatives have been prepared and characterized [3]. However, despite their potential application as a component of functional polymers, there have been a few studies on the incorporation of [2.2]paracyclophane and its derivatives into the conjugated polymer main chain [4]. Recently, we focused our attention on the synthesis of conjugated polymers comprising [2.2]paracyclophane as the repeating unit in their main chain [5–7]. This synthesis would give rise to a whole new class of conjugated polymers in which the conjugation length is extended via the through-space interaction of the benzene rings. In previous studies, pseudo-*para*-disubstituted [2.2]paracyclophane was used as the key monomer in the construction of a through-space conjugated framework [5–7].

The following are seven isomers of the disubstituted [2.2]paracyclophane: *ortho*-, *meta*-, *para*-, pseudo-*ortho*-, pseudo-*meta*-, pseudo-*para*-, and pseudo-*geminal*-disubstituted [2.2]paracyclophanes. Among these isomers, pseudo-*para*-dibromo[2.2]paracyclophane can be easily obtained from commercially available [2.2]paracyclophane [8]. Thermal isomerization of pseudo-*para*-dibromo[2.2]paracyclophane thus obtained conveniently affords pseudo-*ortho*-dibromo[2.2]paracyclophane [8,9]. Therefore, we decided to employ pseudo-*ortho*-linked [2.2]paracyclophane as a building block for through-space

conjugated polymers. In this report, we describe the synthesis of novel through-space conjugated polymers comprising pseudo-*ortho*-linked [2.2]paracyclophane in the main chain and compare the obtained polymer with the polymers possessing the pseudo-*para*-linked [2.2]paracyclophane units.

Experimental

General

^1H and ^{13}C NMR were recorded on a JEOL EX270 and 400 instrument at 270 and 400 MHz and 67.5 and 100 MHz, respectively. All samples were analyzed in CDCl_3 , and chemical shift values were expressed relative to Me_4Si as an internal standard. UV-vis measurements were carried out on JASCO V-530 spectrophotometer at room temperature. Photoluminescence spectra were recorded on a Perkin-Elmer LS50B luminescence spectrometer at room temperature. Gel permeation chromatography (GPC) was carried out on a TOSOH UV-8020 and RI-8020 (TOSOH TSKgel G3000 column) using CHCl_3 as an eluent after calibration with standard polystyrene. Recyclable preparative high-performance liquid chromatography (HPLC) was performed for further purification of polymers on a Japan Analytical Industry Co. Ltd., Model 918R (JAIGEL-2.5H and 3H columns) using CHCl_3 as an eluent. Elemental analyses were performed at the Microanalytical Center of Kyoto University.

Materials

Et_2O , THF and NEt_3 were purified by passage through solvent purification columns under Ar pressure [10]. [2.2]Paracyclophane **1** was purchased from Sigma-Aldrich Co. *n*-BuLi (1.59 M in hexane) was purchased from Kanto Chemical Co., Inc. CH_2Cl_2 , CCl_4 , Br_2 , Fe, triglyme, *t*-BuOK, and CuI were purchased from Wako Pure Chemicals Industries. $\text{Pd}(\text{PPh}_3)_4$ was purchased from Tokyo Chemical Industry Co., Ltd. Pseudo-*para*-dibromo[2.2]paracyclophane **2** [8], pseudo-*ortho*-dibromo[2.2]paracyclophane **3** [9], dibromomethyltriphenylphosphonium bromide [11], pseudo-*ortho*-diethynyl[2.2]paracyclophane **5** [9c], 2,5-dialkoxy-1,4-diiodobenzenes **6a-c** [12], and pseudo-*para*-diethynyl[2.2]paracyclophane **9** [6f] were synthesized according to the literature. Pseudo-*ortho*-diformyl[2.2]paracyclophane **4** was synthesized according to the literature with minor modification by using DMF as a reagent for formylation instead of formylpiperidine [9c], and the spectral data were matched with the literature's values [9c].

Polymerization

All of the solid reagents **5** (40 μmol), **6** (40 μmol), $\text{Pd}(\text{PPh}_3)_4$ (9.2 mg, 8 μmol), and CuI (1.5 mg, 8 μmol) were placed in a Schlenk tube equipped with a magnetic stirring bar and a three-way cock. This tube was then purged with Ar followed by introducing THF (1.2 mL) and Et_3N (1.2 mL). The reaction was carried out at 75°C for 48 h. After the reaction, ammonium salt was filtered off with celite and washed with THF. The combined organic solution was concentrated and washed with aqueous NH_3 solution (28%) to remove the inorganic species. The organic layer was dried over Na_2SO_4 . The condensed organic layer was reprecipitated from EtOH, and

further reprecipitation from $\text{CHCl}_3/\text{EtOH}$ was carried out at least three times to obtain the corresponding polymer as a yellow solid. Further purification by HPLC was carried out for polymers **7b** and **7c**.

7a. Yield: 58%. ^1H NMR (400 MHz, CDCl_3): δ 0.79 (s, 6H), 1.20 (m, 16H), 1.45 (s, 4H), 1.82 (m, 4H), 2.85 (br, 2H), 3.04 (br, 2H), 3.30 (br, 2H), 3.79 (br, 2H), 3.91 (br, 4H), 6.53 (br, 4H), 7.00 (m, 2H), 7.20 (m, 2H). ^{13}C NMR (100 MHz, CDCl_3): δ 14.1, 22.6, 26.3, 29.3, 29.6 (overlapping signals), 31.9, 33.6, 34.4, 69.4, 89.9, 95.0, 114.0, 116.1, 125.2, 132.9, 133.4, 134.1, 139.7, 142.2, 153.5.

7b. Yield: 23%. ^1H NMR (400 MHz, CDCl_3): δ 0.85 (s, 6H), 1.22 (m, 32H), 1.44 (s, 4H), 1.83 (m, 4H), 2.86 (br, 2H), 3.04 (br, 2H), 3.30 (br, 2H), 3.79 (br, 2H), 3.91 (br, 4H), 6.54 (br, 4H), 6.99 (m, 2H), 7.21 (m, 2H). ^{13}C NMR (100 MHz, CDCl_3): δ 14.1, 22.7, 26.4, 29.2, 29.4, 29.7 (overlapping signals), 31.9, 33.7, 34.4, 69.4, 90.0, 94.9, 114.0, 116.2, 125.3, 132.9, 133.4, 134.2, 139.7, 142.3, 153.5.

7c. Yield: 18%. ^1H NMR (400 MHz, CDCl_3): δ 0.87 (s, 6H), 1.25 (m, 48H), 1.44 (s, 4H), 1.83 (m, 4H), 2.86 (br, 2H), 3.04 (br, 2H), 3.30 (br, 2H), 3.80 (br, 2H), 3.90 (br, 4H), 6.54 (br, 4H), 6.99 (m, 2H), 7.21 (m, 2H). ^{13}C NMR (100 MHz, CDCl_3): δ 14.1, 22.7, 26.4, 29.4, 29.7, 29.8 (overlapping signals), 32.0, 33.7, 34.4, 69.4, 90.0, 95.0, 114.1, 116.1, 125.3, 133.0, 133.4, 134.2, 139.7, 142.3, 153.6.

Model compound **8**

Ethynylxylene (0.32 g, 2.5 mmol), **6c** (0.70 g, 1.0 mmol), $\text{PdCl}_2(\text{PPh}_3)_2$ (71 mg, 0.10 mmol), and CuI (18 mg, 0.090 mmol) were placed in a Schlenk tube equipped with a magnetic stirring bar and a three-way cock. This tube was then purged with Ar followed by introducing THF (5.0 mL) and Et_3N (2.0 mL). The reaction was carried out at 50°C overnight. After the reaction, ammonium salt was filtered off. The filtrate was dried and washed with MeOH. The residue was subjected to SiO_2 column (hexane/ CH_2Cl_2 , v/v = 4/1 as an eluent) to afford **8** as a pale yellow solid (0.57 g, 0.81 mmol, 81%).

R_f = 0.33 (SiO_2 , hexane/ CH_2Cl_2 , v/v = 4/1). ^1H NMR (270 MHz, CDCl_3): δ 0.88 (t, J = 7.6 Hz, 6H), 1.25–1.36 (m, 32H), 1.51 (m, 4H), 1.84 (m, J = 6.4 Hz, 4H), 2.31 (s, 3H), 2.51 (s, 3H), 4.02 (t, J = 6.4 Hz, 4H), 7.00 (s, 2H), 7.04 (d, J = 8.0 Hz, 2H), 7.22 (d, J = 8.0 Hz, 2H), 7.33 (s, 2H). ^{13}C NMR (67.5 MHz, CDCl_3): δ 14.1, 20.2, 20.7, 22.7, 26.1, 29.3, 29.5, 29.6 (overlapping signals), 31.9, 69.5, 89.6, 94.1, 114.0, 116.5, 129.1, 129.3, 132.3, 134.9, 137.2, 153.5. Anal. Calcd. for $\text{C}_{50}\text{H}_{70}\text{O}_2$: C, 85.41; H, 10.04. Found: C, 85.32; H, 10.15.

Polymer **10**


Pseudo-*para*-diethynyl[2.2]paracyclophane **9** (10.3 mg, 40 μmol), **6b** (33.5 mg, 48 μmol), $\text{Pd}(\text{PPh}_3)_4$ (9.2 mg, 8 μmol), and CuI (1.5 mg, 8 μmol) were placed in a Schlenk tube equipped with a magnetic stirring bar and a three-way cock. This tube was then purged with Ar followed by introducing THF (1.2 mL) and Et_3N (1.2 mL). The reaction was carried out at 75°C for 48 h. After the reaction, ammonium salt was filtered off with celite and washed with THF. The combined organic solution was concentrated and washed with aqueous NH_3 solution (28%) to remove the inorganic species. The organic layer was dried over Na_2SO_4 . The condensed organic layer was reprecipitated from EtOH, and further reprecipitation from

CHCl₃/EtOH was carried out to obtain the corresponding polymer **10** as a yellow solid (18.4 mg, 26.4 μmol, 66%).


¹H NMR (270 MHz, CDCl₃): δ 0.89 (br, 6H), 1.25-1.59 (br, 36H), 1.96 (br, 4H), 2.94-3.05 (m, 4H), 3.36 (m, 2H), 3.82 (m, 2H), 4.14 (br, 4H), 6.43-6.55 (m, 4H), 7.06-7.16 (m, 4H). ¹³C NMR (67.5 MHz, CDCl₃): δ 14.1, 22.7, 26.3, 29.7 (overlapping signals), 31.9, 34.1, 34.2, 69.6, 89.6, 95.2, 114.0, 116.3, 125.0, 130.3, 133.3, 137.2, 139.6, 142.2, 153.6.

Results and Discussion

Scheme 1 outlines the synthetic procedure for the key monomer, pseudo-*ortho*-diethynyl[2.2]paracyclophane **5**. Iron-catalyzed bromination of [2.2]paracyclophane **1** and successive recrystallization afforded only pseudo-*para*-dibromo[2.2]paracyclophane **2** in 21% yield [8]. Pseudo-*ortho*-dibromo[2.2]paracyclophane **3** was obtained in 59% yield by the thermal isomerization of **2** at 220°C in triglyme [9]. Pseudo-*ortho*-diformyl[2.2]paracyclophane **4** was synthesized by treating **3** with *n*-BuLi and DMF in succession. Diformyl compound **4** was converted to pseudo-*ortho*-diethynyl[2.2]paracyclophane **5**, by a method previously reported by Hopf and coworkers [9c]. Comonomers **6a–c** were synthesized according to the literature's procedure [12].



Scheme 1. Synthesis of monomer **5**



Scheme 2. Synthesis of polymers **7a–c**

Polymerization was carried out via the Sonogashira coupling reaction, as shown in Scheme 2, and the results are summarized in Table 1. Treatment of monomers **5** and **6a–c** with a catalytic amount of Pd(PPh₃)₄/CuI in THF–Et₃N yielded the corresponding polymers **7a–c** in 58%, 23%, and 18% yields, respectively. Repeated purification of the crude polymers **7a–c** by reprecipitation from a CHCl₃/EtOH solution resulted in moderate yields. Further purification by HPLC was carried out for polymers **7b** and **7c**. The molecular weights of the polymers were measured by GPC (CHCl₃: eluent) and estimated by using polystyrene standards (Table 1). The obtained polymers were dissolved in common organic solvents such as CHCl₃, CH₂Cl₂, THF, and toluene. Thin films of these polymers were readily obtained by casting and spin-coating from one of the above mentioned solvents.

Table 1. Results of polymerization

Run	Polymer	Yield ^a %	M_n^b	M_w^b	M_w/M_n^b
1	7a	58	2000	3100	1.6
2	7b	23	3800	4900	1.3
3	7c	18	6400	8800	1.4

^a Isolated yield after reprecipitation at least three times.

^b GPC (CHCl₃), polystyrene standards.






Figure 1. (A) ¹H NMR and (B) ¹³C NMR spectra of polymer **7a** in CDCl₃.

The structures of polymers **7a–c** were confirmed by ¹H and ¹³C NMR spectra. Figure 1 shows the ¹H and ¹³C NMR spectra of polymer **7a** in CDCl₃ (400 MHz and

100 MHz, respectively). In the ^1H NMR spectrum of **7a** (Figure 1A), the signal due to the acetylene proton of monomer **5** at 3.28 ppm completely disappeared, indicating the presence of dialkoxyphenyl moieties at the ends of the polymer chain. Signals at 0.8 ppm, 1.1–1.9 ppm, and 3.9 ppm were assignable to the $-\text{Me}$, $-(\text{CH}_2)_6-$, and $-\text{OCH}_2-$ groups of the alkoxy side chains, respectively. The peaks of the bridged methylene protons belonging to the [2.2]paracyclophane units were observed at 2.8–3.8 ppm as four broad signals. Signals due to the aromatic protons in the [2.2]paracyclophane moieties appeared at 6.5 and 7.0 ppm, and aromatic protons in the alkoxybenzene units were observed at 7.2 ppm. In the ^{13}C NMR spectrum, typical signals of the carbon-carbon triple bond were observed at 90 and 95 ppm, as shown in Figure 1B.

The optical characteristics of the polymers **7a–c** were studied with the spectrophotometer and luminescence spectrometer; and compared with those of model compound **8** and through-space conjugated polymer **10** consisting of pseudo-*para*-linked [2.2]paracyclophane. Polymer **10** was synthesized in 66% yield ($M_n = 6100$) as shown in Scheme 3. The optical behaviors of polymers **7a–c** were identical irrespective of the length of their alkyl side chains. A summary of the optical properties is listed in Table 2. Figures 2 and 3 show the absorption and emission spectra of **7b**, **8**, and **10** in dilute CHCl_3 . As shown in Figure 2, polymer **10**, which possesses the pseudo-*para*-linked [2.2]paracyclophane moiety, had the highest absorption maximum at 386 nm. This was red-shifted relative to polymer **7b** and compound **8**. However, the absorption spectra of polymers **7b** and **10** exhibited no perceptible difference, while the spectrum of **7b** exhibited a red-shift relative to that of **8**. These observations are a direct consequence of the introduction of pseudo-*ortho*-linked [2.2]paracyclophane units into the polymer backbone, which resulted in the through-space conjugation in polymer **7b**.



Scheme 3. Synthesis of polymer **10** containing pseudo-*para*-linked [2.2]paracyclophane

As can be seen from Figure 3, the fluorescence emission spectra of polymers **7b** and **10** were almost similar, and an intense blue emission could be observed for both these polymers. The fluorescence quantum efficiencies of polymers **7b** and **10** were found to be 0.86 and 0.82 (Runs 1 and 3, in Table 2), respectively, which were estimated from the quantum efficiency of the standard compound 9-anthracenecarboxylic acid. The fluorescence emission spectra of **7b** and **10** were also red-shifted relative to the spectrum of model compound **8**.

Table 2. Optical properties of **7b**, **8**, and **10**

Run	Compound	Absorption ^a / nm	Emission ^b / nm	Quantum efficiency ^c
1	polymer 7b	319, 377	411, 434	0.86
2	8	320, 369	398, 417	0.86
3	polymer 10	319, 386	414, 438	0.82

^a In CHCl₃, 1.0×10^{-5} M.

^b In CHCl₃, 1.0×10^{-7} M.

^c Relative efficiency calculated by using 9-anthracenecarboxylic acid as a standard.

On the other hand, the emission spectra of polymers **7b** and **10** exhibited a clear vibrational structure, similar to the emission spectrum of **8** despite their π -stacked structures (Figure 3). This result indicates that polymers **7b** and **10** emit blue light in their monomer state rather than in the phane state. In other words, the emission observed in the case of polymers **7b** and **10** is not from the excimer but from the localized monomer unit [2e–g]. The emission spectrum of thin film of polymer **7b** was broad and red-shifted by approximately 40 nm ($\lambda_{\text{max}} = 471$ nm) relative to that of **7b** in solution owing to the intermolecular π - π interactions (Figure 3).




Figure 2. UV-vis absorption spectra of **7b**, **8**, and **10** in CHCl₃ (1.0×10^{-5} M).




Figure 3. Fluorescence emission spectra of **7b** in CHCl₃ (1.0×10^{-7} M) and film, **8** in CHCl₃ (1.0×10^{-7} M), and **10** in CHCl₃ (1.0×10^{-7} M) excited at each absorption maximum.

Conclusion

Through-space conjugated polymers consisting of pseudo-*ortho*-linked [2.2]paracyclophane were synthesized by the Sonogashira coupling reaction. The polymers exhibited an extension in the conjugation length via the through-space interaction of the [2.2]paracyclophane unit. An intense blue emission with a fluorescence quantum efficiency of 0.86 was observed from the localized monomer state of the polymer, irrespective of the π -stacked structure in the polymer chain. The optical profiles of these polymers were similar to those of the pseudo-*para*

analogues; pseudo-*ortho*-disubstituted [2.2]paracyclophane can be used to synthesize foldamers and hold attraction of planar chirality. Our future research will be focused on synthesizing optically active through-space conjugated polymers with planar-chiral pseudo-*ortho*-linked [2.2]paracyclophane and investigating the higher-ordered structures of foldamers.

Acknowledgements. This work was supported by Grant-in-Aid for Creative Scientific Research of "Invention of Conjugated Electronic Structures and Novel Functions", No. 16GS0209, from the Ministry of Education, Culture, Sports, Science, and Technology, Japan.

References

1. Brown CJ, Farthing, AC (1949) Nature 164:915
2. (a) Cram DJ, Allinger, NL, Steinberg, H (1954) J Am Chem Soc 76:6132 (b) Heilbronner E, Yang ZZ (1983) Top Curr Chem 115:1 (c) Ganuto S, Zerner MC (1990) J Am Chem Soc 112:2114 (d) Yamakita Y, Yamauchi M, Ohno K (2000) Chem Phys Lett 322:189 (e) Oldham Jr WJ, Miao YJ, Lachicotte RJ, Bazan GC (1998) J Am Chem Soc 120:419 (f) Bazan GC, Oldham Jr WJ, Lachicotte RJ, Tretiak S, Chernyak V, Mukamel S (1998) J Am Chem Soc 120:9188 (g) Wang S, Bazan GC, Tretiak S, Mukamel S (2000) J Am Chem Soc 122:1289
3. (a) Vögtle F (1993) Cyclophane Chemistry. Wiley&Sons, New York (b) Shultz J, Vögtle F (1994) Top Curr Chem 172:42 (c) Cleiter R, Hopf H, Eds. (2004) Modern Cyclophane Chemistry. Wiley-VCH, Weinheim
4. (a) Salhi F, Collard DM (2002) Polym Mater Sci Eng 222 (b) Salhi F, Collard DM (2003) Adv Mater 15:81 (c) Guyard L, Audebert P (2001) Electrochem Commun 3:164 (d) Guyard L, Nguyen Dinh An M, Audebert P (2001) Adv Mater 13:133
5. (a) Morisaki Y, Chujo Y (2006) Angew Chem Int Ed 45:6430 (b) Morisaki Y, Chujo Y (2008) Prog Polym Sci 33:346
6. (a) Morisaki Y, Chujo Y (2002) Macromolecules 35:587 (b) Morisaki Y, Chujo Y (2002) Chem Lett 194 (c) Morisaki Y, Ishida T, Chujo Y (2002) Macromolecules 35:7872 (d) Morisaki Y, Chujo Y (2002) Polym Bull 49:209 (e) Morisaki Y, Fujimura F, Chujo Y (2003) Organometallics 22:3553 (f) Morisaki Y, Chujo Y (2003) Macromolecules 36:9319 (g) Morisaki Y, Chujo Y (2004) Macromolecules 37:4099 (h) Morisaki Y, Ishida T, Tanaka H, Chujo Y (2004) J Polym Sci Part A Polym Chem 42:5891 (i) Morisaki Y, Wada N, Chujo Y (2005) Polym Bull 53:73 (j) Morisaki Y, Wada N, Chujo Y (2005) Polymer 46:5884 (k) Morisaki Y, Chujo Y (2005) Bull Chem Soc Jpn 78:288
7. (a) Morisaki Y, Chujo Y (2005) Tetrahedron Lett 46:2533 (b) Morisaki Y, Murakami T, Chujo Y (2008) Macromolecules 41:5960
8. Reich HJ, Cram DJ (1969) J Am Chem Soc 91:3527
9. (a) Pye PJ, Rossen K, Reamer RA, Tsou NN, Volante RP, Reider PJ (1997) J Am Chem Soc 119:6207 (b) Braddock DC, MacGilp ID, Perry BG (2002) J Org Chem 67:8679 (c) Bondarenko L, Dix I, Hinrichs H, Hopf H (2004) 16:2751
10. Pangborn AB, Giardello MA, Grubbs RH, Rosen RK, Timmers FJ (1996) Organometallics 15:1518
11. Wolkoff P (1975) Can J Chem 53:1333
12. Li H, Powell DR, Hayashi RK, West R (1998) Macromolecules 31:52